

- Certificate / ProductInformation -

RAVENOL SCOOTER 2-Takt Fullsynth.

Art. 1151150

Description:

RAVENOL SCOOTER 2-Takt Fullsynth. is high quality fully synthetic two-stroke engine oil.

RAVENOL SCOOTER 2-Takt Fullsynth. with special esters and Polyisobutylene (PIB) and effectively low ash additives for optimum protection against wear and prevent corrosion, deposits and auto-ignitions, even with heavy loads.

RAVENOL SCOOTER 2-Takt Fullsynth. is optimized for air- and watercooled two stroke engines in Scooters.

Application Directions:

RAVENOL SCOOTER 2-Takt Fullsynth. can generally be mixed with regular petrol 1:100.

RAVENOL SCOOTER 2-Takt Fullsynth. is best choice for air- and watercooled two stroke engines in Scooters.

RAVENOL SCOOTER 2-Takt Fullsynth. is used for lubrication of air-cooled two-stroke petrol engines with very high speed and heaviest load.

RAVENOL SCOOTER 2-Takt Fullsynth. is also suitable for the lubrication of two stroke scooters with water cooling. Suitable for separate lubrication systems and self-mixing systems.

Quality Classification:

RAVENOL SCOOTER 2-Takt Fullsynth. is approved, tried and tested for aggregates specifying:

Specifications: API TD, ISO-L-EGD

Fulfils: JASO FD, Approval JASO 049RAV153

Recommendations: Aprilia, Honda, Kymco, Peugeot, Piaggio, Suzuki, Vespa, Yamaha

Technical Characteristics:

RAVENOL SCOOTER 2-Takt Fullsynth. offers:

- A proper lubrication of all engine parts
- A strong cleaning effect, for clean combustion chambers. Cleans intake and exhaust ports from combustion residues and deposits
- Clean spark plugs provide optimal performance of the engines
- A very high wear and corrosion protection
- Low exhaust emission levels by good combustion

Technical Values:

Characteristics		unit	data	test according to
Colour			red	visual
Density	at 20°C	kg/m ³	869	EN ISO 12185
Viscosity	at 40°C	mm ² /s	48,0	DIN 51 562
	at 100°C	mm ² /s	8,0	DIN 51 562
Viscosity index VI			138	DIN ISO 2909
Flash point (COC)		°C	110	DIN ISO 2592
Pour point		°C	- 21	DIN ISO 3016
TBN		mg KOH/g	2,4	DIN ISO 3771
Sulphated ash		% wt.	<0,04	DIN 51 575

All indicated data are approximate values and are subject to the commercial fluctuations.