

Ravensberger Schmierstoffvertrieb GmbH
PO box 1163
D-33819 Werther
Tel.: +49 5203/9719-0
Fax.: +49 5203/9719-40 / 41

-Certificate/Product Information-

RAVENOL Motobike V-Twin SAE 20W-50 Fullsynth.

Art. 1171105

MOTOBIKE

Description:

RAVENOL Motobike V-Twin SAE 20W-50 Fullsynth. is a high grade, fully-synthetic 3-in-1 lubricant for engine, drive and crank shaft, that was specially designed for cruiser and chopper motorcycles. Thanks to its synthetic components and specifically attuned, innovative additives, it is excellently suited for the demanding engines, drives and crankshafts of cruise and chopper motorcycles.

RAVENOL Motobike V-Twin SAE 20W-50 Fullsynth. reduces the friction and reliably protects the valves and the crankshaft against metal-to-metal contact. The consistent viscosity reduces load peaks at high temperatures.

RAVENOL Motobike V-Twin SAE 20W-50 Fullsynth. demonstrates excellent stability and durability against thermal loads under extremely high temperatures that can occur in air-cooled V-twin engines.

Application Directions:

RAVENOL Motobike V-Twin SAE 20W-50 Fullsynth. is suitable as an engine oil for all V-twin chopper und cruiser motorcycles if the specification SAE 20W-50 is required.

Quality Classification:

RAVENOL Motobike V-Twin SAE 20W-50 Fullsynth. is tried and tested for aggregates specifying:

Tried and tested for cruiser and chopper motorcycles

Recommendations: BMW Cruiser motorcycles

Harley Davidson 62600005, 62600031

Honda 08C35-A251M01, 08C35-A251L01

Indian motorcycles, Victory motorcycles

Yamalube LUB20W50AP04, LUB20W50AP12

Triumph motorcycles, Moto Guzzi motorcycles

Suzuki V-twin motor oil

Technical Characteristics:

RAVENOL Motobike V-Twin SAE 20W-50 Fullsynth. offers:

- a very stable and outstanding viscosity behaviour
- reduced friction
- outstanding viscosity temperature characteristics
- a reliable lubrication film at extremely high operating temperatures
- very good protection against wear and corrosion
- protection against foaming
- excellent deterging and dispersing properties

Technical Values:

Characteristics		unit	data	test according to
Colour			brown	visual
Density	at 20°C	kg/m ³	858	EN ISO 12185
Viscosity	at -15°C	mPa*s	4473	ASTM D5293
	at 40°C	mm ² /s	139.67	DIN 51 562
	at 100°C	mm ² /s	19.8	DIN 51 562
Viscosity index VI			163	DIN ISO 2909
Flash point (COC)		°C	252	DIN ISO 2592
Pour point		°C	-42	DIN ISO 3016
TBN		mg KOH/g	7.4	DIN ISO 3771

All indicated data are approximate values and are subject to commercial fluctuations..

To the best of our knowledge all information reflects the current state of findings and our development. Subject to change. Any reference to DIN standards are solely for product description purposes and do not represent a guarantee. If problems occur please consult a technician.

11.09.15